

ANNEXURE

1. Woolen Blanket -Variety 1 and corresponding specification

Item	Length & Breadth (m)	Yarn Count Warp x Weft	Composition (% of blend)	Thread/inch (Warp) X (Weft)	Average GSM (Min. Max)	Wash Fastness	Max. Shrinkage allowed (On washing)	Design
Woolen Blanket	2.3 X 1.5 L : As marked B: (-) 2% tol		Min. Wool : 80%	--	685 & above	Not applicable	--	Deep Multicoloured body with pico/fringes on both sides of the border

2. Woolen Blanket -Variety 2 and corresponding specification

Item	Corresponding BIS Number	Length & Breadth (m)	Yarn Count Warp x Weft	Composition (% of blend)	Thread/inch (Warp) X (Weft)	Border width count of Border Yarn	Average GSM (Min. Max)	Color Fastness to Washing	Color fastness to light	Color fastness to Dry Rubbing	Color fastness to Wet Rubbing	Max. Shrinkage allowed (On washing) (on Soaking)	Design	Remark
Woolen Blanket	IS : 894 : 1980	2.3 X 1.5 L : As marked B: (-) 2% tol		Min. Wool : 80%, 20% Acrylic (Test method to be followed as specified in IS : 1349-1964)	22 X 22 (Test method to be followed as specified in IS : 1963-19810)		700 & above (Blanket weight 2.4 kg) (Test method to be followed as specified in IS 1964: 2001)	4 & above (Test method to be followed as per specified in IS 687 : 1966)	4 & above (Test method to be followed as per specified in IS 2454:1985)	4 & above (Test method to be followed as per specified in IS 766: 1988)	3 & above (Test method to be followed as per specified in IS 766: 1988)	4% both in Warp & Weft direction (Test method to be followed as specified in IS 665:1962)	Deep Multicoloured body with pico/fringes on both sides of the border 2/2 twill weave	No banned & hazardous dyes and chemical shall be used, as per standards regulations

Criterion for Conformity : Each test specimen must meet all the specified values

3. Woolen Blanket -Variety 3 and corresponding specification

Item	Length & Breadth (m)	Composition (% of blend)	Thread/inch (Warp) X (Weft)	Average GSM (Min. Max)	Color Fastness to Washing	Max. Shrinkage allowed (On washing) (on Soaking)	Design	Remark
Woolen Blanket	2.3 X 1.5 L : As marked B: (-) 2% tol	Min. Wool : 80%, 20% other synthetic fiber including acrylic	22 X 22	700 & above (Blanket weight 2.4 kg)	4 & above	4% both in Warp & Weft direction	Deep Multicoloured body with pico/fringes on both sides of the border 2/2 twill weave	No banned & hazardous dyes and chemical shall be used, as per standers regulations